

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 63-072777

(43)Date of publication of application : 02.04.1988

(51)Int.Cl.

C09J 7/02

B32B 5/08

B32B 27/12

D04D 9/00

(21)Application number : 61-218478

(71)Applicant : NITTO ELECTRIC IND CO
LTD

(22)Date of filing : 16.09.1986

(72)Inventor : MIKI YOSHIO
OCHIUMI TSUKASA
MORIOKA AKIRA
ARAI TAKEHIKO
KAMEI KIYOHIRO

(54) ADHESIVE TAPE

(57)Abstract:

PURPOSE: To improve water resistance and tearability and to reduce weight and cost, by using specified materials for warps and wefts constituting the base of an adhesive tape and providing a synthetic resin laminate layer on at least one side of the base.

CONSTITUTION: This adhesive tape is provided with an adhesive layer on at least one side of a base woven of warps and wefts. In the base, the warp is formed from a polyolefin multifilament (a) and the weft is formed from a high-melting multifilament contg. a monofilament (b) having an m.p. higher by at least 10°C than that of said polyolefin multifilament. A synthetic resin laminate layer is provided on at least one side of the base. A preferred example of the component (a) is a polypropylene multifilament. Preferred examples of the component (b) are polyester, polyamide and acrylic monofilaments.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

**[Number of appeal against examiner's
decision of rejection]**

**[Date of requesting appeal against examiner's
decision of rejection]**

[Date of extinction of right]

Copyright (C); 1998,2000 Japan Patent Office

Thema:

Thermopla nd „extrusion coating“ (Patente)

AN 1988-129622 [19] WPINDEX

DNN N1988-098493 DNC C1988-058134

TI Tearable adhesive tape - comprises woven wefts and warps of poly olefin multifilament wool with different m.pt. and resin layer.

DC A81 F03 G03 P73

PA (NITL) NITTO ELECTRIC IND CO

CYC 1

PI JP--63072777 A 19880402 (198819)* 4p

ADT JP--63072777 A 1986JP-0218478 19860916

PRAI 1986JP-0218478 19860916

IC B32B-005-08; B32B-027-12; C09J-007-02; D04D-009-00

AB JP 63072777 A UPAB: 19930923

Tearable adhesive tape comprises adhesive layer(s) provided on the surface(s) of woven substrate tape comprising weft of poly-olefin multifilaments and warp of high m.pt. multifilaments containing monofilaments having m.pt. higher by at least 10 deg.C. than that of the polyolefin multifilaments are laminated with synthetic resin layer on the surface(s) of woven substrate.

The polyolefin is pref. polyethylene, polypropylene or polybutene-1 having density = 0.91-0.97 g/cm³. or ethylene/propylene copolymer, etc. The multifilaments for weft comprise 1-10 denier-monofilaments and have total fineness = 30-200 denier. The multifilaments for the warp comprise monofilaments of polyester, polyamide, polyvinyl chloride, polyacrylate, polyvinyl alcohol, polyvinylidene chloride polyacrylonitrile or polypropylene and have total fineness = 30-500 denier. The substrate tape comprises warp containing 30-130 multifilaments/inch and weft containing 30-100 multifilaments/inch. The laminating film is olefinic (co)polymer or other thermoplastic resin and laminated on the substrate tape by extrusion or melt coating to a thickness of 5-80 microns.

USE/ADVANTAGE - The adhesive tape has high water resistance and it is tearable easily and linearly with fingers.

0/0

FS CPI GMPI

FA AB

MC CPI: A04-G01E; A12-A01; A12-S05F; F02-A03A; F02-E03; F03-E01; F04-E; G03-B04

This Page Blank (uspto)